

# Supershield 430-0

Ferritic STS Type

## Conformances


## Applications

- Continuous casting rolls, steel mill rolls

## Features

- Open arc type hardfacing wire(build-up)
- Ferritic stainless steel type

## Welding Position



## Current

DC +

## Welding Process

Open Arc

## Diameter / Packaging

Diameter mm (in)	Coil	Pac	
	25kg (55lbs)	150kg (330lbs)	250kg (551lbs)
2.4 (3/32)	✓	✓	✓
2.8 (7/64)	✓	✓	✓

## Typical Chemical Composition of All-Weld Metal (%)

	C	Si	Mn	Cr
As welded with 2.4/2.8mm wire	0.05	0.7	0.9	17.0

## Typical Mechanical Properties of All-Weld Metal

	Rockwell Hardness(HRC) (≥3layers)
On Mild Steel (2.4/2.8mm)	5-10

## Typical Welding Parameters

Diameter, Polarity Shielding Gas	CTWD mm (in)	Wire Feed Speed m/min (in/min)	Amp. (A)	Volt. (V)	Deposition Rate kg/hr (lb/hr)
<b>2.8mm (7/64in), DC+</b>					
Open Arc	25 (1)	2.9 (114)	330	27	4.9 (10.8)
		3.3 (130)	360	29	5.6 (12.3)
		3.8 (149)	400	30	6.5 (14.2)

SMW

SAW

GMAW

GTAW

FCAW

Non-FERROUS

APPENDIX